

A.4 Composition of Metallic and Other Materials

TABLE A.4

Composition of Metallic and Other Materials

| <i>No.</i> | <i>Material</i> | <i>Manufacturer</i> | <i>Composition or Description</i> |
|---------------|--------------------------------------|--------------------------|--|
| <i>Metals</i> | | | |
| 17 | Aluminum | | |
| 19 | Aloyco-20 | Alloy Steel Products Co. | Fe; 19–21 Cr; 28–30 Ni; 4.0–4.5 Cu; 2.5–3.0 Mo; 1.5 max. Si; 0.65–0.85 Mn; 0.07 max. C |
| 19a | 720 Alloy | General Plate | 20 Mn; 20 Ni; Cu |
| 54–60 | Brass | | Various commercial grades ranging 60–65 Cu; 35–40 Zn; 0.5–3.0 Pb |
| 63 | Brass, red | | 85 Cu; 15 Zn |
| 66 | Bronze, comm. | | 90 Cu; 10 Zn |
| 73 | Bronze, phosphor, 5% A | | 94.8–95.5 Cu; 4.3–5 Sn; P |
| 74 | Bronze, phosphor, 8% C | | Cu; 7–9 Sn; 0.03–0.25 P |
| 75 | Bronze, phosphor 10% D | | 89.5–90 Cu; 10–10.5 Sn; P |
| 76 | Bronze, phosphor, spec. free cutting | | 88 Cu; 4 Zn; 4 Sn; 4 Pb |
| 81 | CA-FA20 | Cooper Alloy | Fe; 19–21 Cr; 28–30 Ni; 3.5 Mo; 4–4.5 Cu; 0.07 max. C |
| 82 | CA-MM | Cooper Alloy | 67 Ni; 30 Cu; 1.4 Fe; 0.1 Si; 0.15 C |
| 86 | Cast iron | | Ordinary unalloyed cast iron |
| 88 | Chlorimet 2 | Duriron Co. | 63 Ni; 32 Mo; 3 max. Fe; 0.15 max. C; 1 Si; 1 Mn |
| 89 | Chlorimet 3 | Duriron Co. | 60 Ni; 18 Mo; 18 Cr; 2 Fe; 0.07 max. C; 1 Si; 1 Mn |
| 111 | Copper | | 99.9+ Cu |
| 112 | Copper, Be | | 97.5 Cu; 2.15 Be; 0.35 Ni |
| 119 | Corrosiron | Pacific Fdry. | Fe; 14.5 Si |
| 140 | Durichlor | Duriron Co. | Fe; 0.85 C; 14.5 Si; 3 Mo; 0.35 Mn |
| 141 | Durimet 20 | Duriron Co. | Fe; 20 Cr; 29 Ni; 0.07 max. C; 2 Mo; 4 Cu; 1 Si |
| 142 | Durimet T | Duriron Co. | Fe; 19 Cr; 22 Ni; 0.07 max. C; 2 Mo; 1 Cu; 1 Si |
| 143 | Duriron | Duriron Co. | Fe; 0.80 C; 14.5 Si; 0.35 Mn |
| 148 | Everdur 1000 | Amer. Brass | 94.9 Cu; 4 Si; 1.1 Mn |
| 149 | Everdur 1010 | Amer. Brass | 95.8 Cu; 3.1 Si; 1.1 Mn |
| 150 | Everdur 1015 | Amer. Brass | 98.25 Cu; 1.5 Si; 0.25 Mn |
| 156 | Gold | | 99.99 Au |
| 156a | Green gold | | 75% Au; 25% Ag |
| 159 | Hastelloy A | Haynes Stellite | Ni; 17–21 Mo; 17–21 Fe |
| 160 | Hastelloy B | Haynes Stellite | Ni; 24–32 Mo; 3–7 Fe; 0.02–0.12 C |
| 161 | Hastelloy C | Haynes Stellite | Ni; 14–19 Mo; 4–8 Fe; 0.04–0.15 C; 12–16 Cr; 3–5.5 W |
| 162 | Hastelloy D | Haynes Stellite | Ni; 8–11 Si; 2–5 Cu; 1 max. Al |
| 163 | Stellite 1 | Haynes Stellite | Co; 28–34 Cr; 11–15 W |

TABLE A.4 Continued
Composition of Metallic and Other Materials

| <i>No.</i> | <i>Material</i> | <i>Manufacturer</i> | <i>Composition or Description</i> |
|----------------------------|----------------------|---------------------|--|
| 165 | Stellite 6 | Haynes Stellite | Co; 25–31 Cr; 3–6 W |
| 184 | Inconel | Int'l Nickel | 79.5 Ni; 13 Cr; 6.5 Fe; 0.08 C; 0.2 Cu; 0.25 Mn |
| 191 | Lead | | 99.9 + Pb |
| 192 | Lead, antimonial | | 94 Pb; 6 Sb |
| 193 | Lead, antimonial | | Pb; 4–12 Sb |
| 196 | Lead, chemical | | 99.93 Pb; 0.06 Cu |
| 200 | Lead, Te | | 99.88 Pb; 0.045 Te; 0.06 Cu |
| 216 | Monel | Int'l Nickel | 67 Ni; 30 Cu; 1.4 Fe; 0.1 Si; 0.15 C |
| 219 | Muntz Metal | | 60 Cu; 40 Zn |
| 224 | Nickel | Int'l Nickel | 99.4 Ni; 0.2 Mn; 0.1 Cu; 0.15 Fe; 0.05 Si |
| 224a | Z-Nickel | Int'l Nickel | 95 + Ni |
| 226 | Nickel–Silver 18% A | | 65 Cu; 18 Ni; 17 Zn |
| 227 | Nickel–Silver 18% B | | 55 Cu; 18 Ni; 27 Zn |
| 227a | Ni-Span | Int'l Nickel | Ni, Ti, Cr, C, Mn, Si, Al |
| 229 | Ni-Hard | Int'l Nickel | Fe; 3.4 C; 1.5 Cr; 4.5 Ni; 0.6 Si |
| 231 | Ni-Resist | Int'l Nickel | Fe; 2.8 C; 14 or 20 Ni; 6 Cu (optional); 2 Cr; 2 Si |
| 240 | Platinum | | 99.99 Pt |
| 268 | Silver | | 99.9+ Ag |
| 275 | S.S. 301 | | Fe; 16–18 Cr; 6–8 Ni; 0.08–0.15 C |
| 276 | S.S. 302 | | Fe; 17–19 Cr; 8–10 Ni; 0.08–0.15 C |
| 278 | S.S. 303 | | Fe; 17–19 Cr; 8–10 Ni; 0.15 max. C; 0.07 min. P, S, Se; 0.6 |
| 279 | S.S. 304 | | Fe; 18–20 Cr; 8–11 Ni; 0.08 max. C; 2 max. Mn |
| 282 | S.S. 310 | | Fe; 24–26 Cr; 19–22 Ni; 0.25 max. C |
| 283 | S.S. 316 | | Fe; 16–18 Cr; 10–14 Ni; 0.1 max. C; 1.75–2.75 Mo |
| 284 | S.S. 317 | | Fe; 17.5–20 Cr; 10–14 Ni; 0.1 max. C; 3–4 Mo |
| 285 | S.S. 321 | | Fe; 17–19 Cr; 8–11 Ni; Ti, 5xC min. |
| 286 | S.S. 347 | | Fe; 17–19 Cr; 9–12 Ni; Cb, 10xC min. |
| 287 | S.S. 403 | | Fe; 11.5–13 Cr; 0.15 max. C |
| 290 | S.S. 410 | | Fe; 11.5–13.5 Cr; 0.15 max. C |
| 292 | S.S. 416 | | Fe; 12–14 Cr; 0.15 max. C; 0.07 min. P, S, Se; 0.6 max. Zr, Mo |
| 295 | S.S. 430 | | Fe; 14–18 Cr; 0.12 max. C |
| 303 | S.S. 446 | | Fe; 23–27 Cr; 0.35 max. C; 0.25 max. N |
| 360a | Steel | | Plain carbon steel |
| 368 | Tantalum | Fansteel | 99.9+ Ta |
| 390 | Worhite | Worthington Pump | Fe; 20 Cr; 24 Ni; 0.07 max. C; 3.25 Si; 3 Mo; 1.75 Cu; 0.5 Mn |
| <i>Carbon and Graphite</i> | | | |
| 401 | Karbate (carbon) | National Carbon | Impervious carbon |
| 402 | Karbate (graphite) | National Carbon | Impervious graphite |
| <i>Ceramics</i> | | | |
| 611 | Lapp Porcelain | Lapp Insulator Co. | Chemical porcelain |
| 614 | Pfudler Glass Lining | Pfudler Co. | Glass-lined steel equipment |
| 615 | Plate Glass | | Polished plate glass, flat or bent |
| 616 | Pyrex | Corning Glass Wks. | Glass |

TABLE A.4 Continued
Composition of Metallic and Other Materials

| <i>No.</i> | <i>Material</i> | <i>Manufacturer</i> | <i>Composition or Description</i> |
|-----------------|-----------------|----------------------|---|
| Plastics | | | |
| 700 | Ace Saran | American Hard Rubber | Vinylidene chloride |
| 710 | Geon | B. F. Goodrich | Polyvinyl chloride |
| 711 | Haveg 41 | Haveg Corp. | Phenolic-asbestos |
| 712 | Haveg 43 | Haveg Corp. | Phenolic-graphite |
| 713 | Haveg 60 | Haveg Corp. | Furan-asbestos |
| 714 | Haveg 63 | Haveg Corp. | Furan-graphite |
| 715 | Heresite M 66 | Heresite & Chem. Co. | Transparent molding powder |
| 716 | Heresite MF 66 | Heresite & Chem. Co. | Black molding powder |
| 717a | Kel-F | M. W. Kellogg | Polymerized trifluoroethylene |
| 718 | Koroseal | B. F. Goodrich | Plasticized polyvinyl chloride |
| 731 | Nylon FM-101 | E. I. du Pont | Injection, compression and extrusion moldings (tubing, sheeting, wire covering, gasketing) |
| 731a | Plastisol | | Polyvinyl chloride |
| 735 | Polythene | E.I. du Pont | Polyethylene |
| 740 | Saran | Dow Chemical | Vinyl chloride-vinylidene chloride copolymer |
| 740a | Sirvene | Chicago Rawhide | Synthetic rubber |
| 742 | Teflon | E.I. du Pont | Polymerized tetrafluoroethylene |
| 746 | Tygon | U.S. Stoneware | Synthetic compounds |
| Rubber | | | |
| 800 | Ace Hard Rubber | American Hard Rubber | Vulcanized rubber |
| 805 | Butyl (GR-I) | Stanco Distributors | Solid copolymer of isobutylene and isoprene |
| 820 | Hycar (GR-A) | B. F. Goodrich | Nitrile type synthetic rubber |
| 829 | Neoprene | E. I. du Pont | Polymer of chloroprene |
| 836 | Natural (soft) | | |
| 837 | Natural (hard) | | |
| 838 | GR-S (soft) | | |
| 839 | GR-S (hard) | | |
| 853 | Thiokol (GR-P) | Thiokol Corp. | |